



Profoam Corporation  
 145 Newborn Rd  
 Rutledge, GA 30663  
 www.Profoam.com | 706-557-1400

## TECHNICAL DATA and FACT SHEET

# 11-033 SPRAY FOAM SYSTEM

### DESCRIPTION:

11-033 is a two component, self-adhering, seamless, closed cell, spray applied polyurethane foam system. This Profoam system has been formulated with highly insulating HFO as the blowing agent. The insulation system is suitable for interior building insulation applications in Type I, II, III, IV and V construction.

### DISTINGUISHING CHARACTERISTICS:

- Low GWP
- Passed Appendix X with no Ignition Barrier
- High Yields
- Meets ASTM E84, FS  $\leq 25$ , SD  $\leq 450$  @ 4"
- Air Impermeable Insulation at 1/2"
- Approved with DC315 coating in lieu of code prescribed thermal barrier
- Class II Moisture Vapor Retarder @ 1"
- Approved for use in Type I, II, III, IV, V construction. Contact Profoam regarding the specific approved wall assemblies.

R-Values*		
Thickness (inches)	R-Value (°F-hr-ft <sup>2</sup> / Btu)	Moisture Vapor Perm
1"	7.0	0.947
2"	13	0.474
3"	20	0.316
3.5"	23	0.271
5.5"	37	0.172
6"	40	0.158
7"	47	0.135
8"	53	0.118
9"	60	0.105

\*Note: As with all insulating materials, the R-value will vary with age and use conditions.

### TYPICAL PHYSICAL PROPERTIES\*<sup>1</sup>:

Free Rise Core Density* <sup>2</sup> ASTM D 1622	1.7 pcf
Closed Cell Content ASTM D 6226	> 90%
R-value @ 1" - ASTM C 518	7.0
Air Perm @ 1/2" & 75 Pa ASTM E2178	0.0048 L/(m-s <sup>2</sup> )
Moisture Vapor Perm ASTM E96 @ 1"	0.95 perms
Flammability ASTM E84 @ 4 inches	Flame Spread $\leq 25$ Smoke Dev $\leq 450$
Max Service Temperature	180°F

\*<sup>1</sup>The above values are average values obtained from laboratory experiments and should serve only as guide lines.

\*<sup>2</sup>Free rise core density should not be confused with overall density. Overall densities are always higher than free rise core densities and take into account skin formation, thickness of application, environmental conditions, etc.

For proper use of this Profoam insulating material refer to the Profoam Application Information and any of the following codes or guides:

- 2015 International Building Code Chapter 26 or Residential Code Section R316 & R806
- 2018 International Building Code Chapter 26 or Residential Code Section R316 & R806
- CPI Fire Safety Guidelines for Use of Rigid Polyurethane and Polyisocyanurate Foam Insulation in Building Construction

Polyurethane products manufactured or produced from this liquid system may present a serious fire hazard if improperly used or allowed to remain exposed or unprotected. The character and magnitude of any such hazard will depend on a broad range of factors, which are controlled and influenced by the manufacturing and production process, by the mode of application or installation and by the function and usage of the particular product. **Any flammability rating contained in this literature is not intended to reflect hazards presented by this or any other material under actual fire conditions. These ratings are used solely to measure and describe the product's response to heat and flame under controlled laboratory conditions.** Each person, firm or corporation engaged in the manufacture, production, application, installation or use of any polyurethane product should carefully determine whether there is a potential fire hazard associated with such product in a specific usage, and utilize all appropriate precautionary and safety measures.

## 11-033 Application Information

### STORAGE AND USE OF CHEMICALS:

The 11-033 chemicals should be between 65°F and 80°F for proper processing through the spray equipment. Chemicals shipped during winter or summer months may need extra time in moderate temperature storage to stabilize back in the proper application range. Cold chemicals can cause poor mixing, pump cavitation or other process problems due to higher viscosity at lower temperatures. Storing chemicals above 90°F should be avoided as much as possible.

Excessively warm chemicals should be cooled prior to opening the drums. Do not store in direct sunlight. Keep drums tightly closed when not in use and under dry air or nitrogen pressure of 2-3 psi after they have been opened. The shelf life of 11-033 is six months

### SAFE HANDLING OF LIQUID COMPONENTS:

Use caution in removing bungs from the container. Loosen the small bung first to allow any built-up vapor pressure to stabilize before completely removing. **B component will froth at elevated temperatures.** Avoid prolonged breathing of vapors. In case of chemical contact with eyes, flush with water for at least 15 minutes and get medical attention. For further information refer to [www.spraypolyurethane.org](http://www.spraypolyurethane.org), Resources box, "Health and Safety Product Stewardship Workbook for High-Pressure Application of SPF."

### APPLICATION GUIDELINES:

11-033 is suitable for application to most construction materials including wood, masonry, concrete, and metal. 11-033 should not be applied to surfaces that will be in contact with soil and intermittent contact with water. To ensure proper adhesion, all substrate surfaces should be dry, clean of dust or flaking surface rust, ice or frost. All metal surfaces must be free of oil, grease, etc. Uncoated metals may require a primer coat.

No flammable chemicals, such as wasp and hornet sprays, should be sprayed in the area of the foam application 24 hours before the application. No such chemical can be sprayed after the foam application until the foam has cooled to room temperature.

### APPLICATION AROUND PLASTIC PIPES:

Based on a series of extensive studies, the 11-033 system can be applied in contact with PVC, CPVC, ABS, PP-R and PEX plastic pipes. The pipes must not be pressurized during the foam application. The foam pass applied in contact with the pipe should not exceed 2" thick in order to prevent excessive exothermic heat at the pipe to foam interface. Allow 2 minutes cooling between each additional foam pass. The total foam thickness is limited to that thickness permitted in that area of the building assembly.

### APPLICATION AROUND ELECTRICAL WIRES:

Based on Profoam testing, the 11-033 system can be applied in contact with electrical wires. Spray foam applicators must spray the foam in such a manner that the expanding foam does not stretch and distort the wires. Light gauge wires which will be encapsulated in the foam layer should have the foam installed behind the wires and allowed to cool prior to applying a top layer to cover the wire. Use a shallow lift of 3/4" of foam to cover the wire. Wait the required 2 minutes between passes when adding more foam thickness to achieve the desired R-value.

### APPLICATION PASS THICKNESS:

Spraying foam will generate heat. Foam which is applied too thick in single passes can build temperatures which will degrade cell structure and not produce foam with optimum properties. In the most extreme case, 11-033 could reach dangerously high temperatures inside the finished foam which could lead to splitting, charring, or even spontaneous combustion. The maximum pass thickness for 11-033 is 4 inches. Wait 10 minutes or until the foam surface has cooled to ambient temperature before adding additional foam passes. Multiple layers can be applied to achieve the desired R-value.

### Read This Before You Buy

#### What you should know about R values

The chart shows R value of this insulation. R value means resistance to heat flow. The higher the R value, the greater the insulating power. Compare insulation R values before you buy. There are other factors to consider. The amount of insulation you need depends mainly on the climate you live in. Also, your fuel savings from insulation will depend upon the climate, the type and size of your house, the amount of insulation already in your house, and your fuel use patterns and family size. If you buy too much insulation, it will cost you more than what you'll save on fuel. To get the marked R-value, it is essential that this insulation be installed properly.

## 11-033 Application Information

### EQUIPMENT AND COMPONENT RATIOS:

The 11-033 system, consisting of an A and B component, is formulated for spraying with a two component pump specifically designed for spray polyurethane foam systems. The B drum is connected to the resin pumps and the A drum is connected to the isocyanate pumps. The proportioning pump ratio is 1 to 1. The preheater and hose temperature should be set at 130°F to give a good pattern. Due to equipment variations, the application temperature settings may be adjusted to achieve a good spray pattern. For higher-pressure settings above 1,000 psi, the temperature settings can be slightly lower.

### OPTIMUM ADHESION TEMPERATURE OF SURFACE TO BE SPRAYED:

The surface should be between 40°F and 120°F. In this range the warmer the surface, the better the adhesion. For best results, when surfaces to be sprayed are cooler than 60°F a flash coat should be applied with the second coat following as soon as the original coat is no longer tacky to the touch. In studwall assemblies, spray the cant along the side of the studs before filling in the center of the stud bay.

### BACTERIA AND FUNGUS RESISTANCE:

11-033 is naturally able to inhibit the growth of bacteria and fungus (mold) per the ASTM G-21. The anti-microbial properties do not protect occupants of spaces insulated with 11-033 from potential deleterious effects of molds, mold spores, or disease organisms that may be present in the environment.

### CODE-COMPLIANT FIRE RESISTANCE:

Building Codes require foam plastic insulation, such as 11-033, be separated from the interior of the building by a 15 minute thermal barrier of ½" gypsum board or other approved material. Refer to specific building codes for details. 11-033 has passed testing with the DC315 intumescent coating in lieu of the thermal barrier. When covering with DC315, the maximum foam thickness in walls is 5.5 inches and in roof/ceiling assemblies the maximum foam thickness is 9.5 inches. The DC315 is applied at 14 mils wet film thickness, or 1 gallon per 115 square feet.

### ATTICS and CRAWL SPACES:

11-033 has passed testing for application in limited access attics and crawl spaces without the code prescribed ignition barrier covering. The foam thickness can be up to 8" on wall cavities and 10" in ceiling cavities.

### OTHER APPLICATION AND SAFETY CONSIDERATIONS:

Before 11-033 is to be applied, there are many safety and application situations to consider. All spray foam applicators must evaluate the job prior to beginning the spray foam application. It is impossible to anticipate every issue and provide explicit guidance in this product data sheet. If there is a question regarding some aspect of the planned application, consult with Profoam for more guidance. The Profoam Product Stewardship Manual contains additional information and should be reviewed often enough by all spray foam applicators to remain familiar with the contents. The American Chemistry Council (ACC), the Center for Polyurethanes Industry (CPI) and the Spray Polyurethane Foam Alliance (SPFA) also publish information regarding the safe handling and application of spray foam chemicals. If there are any questions regarding the application of the 11-033 system, contact a Profoam representative.

### VENTILATION OF SPRAY AREA:

Spraying foam will generate a mist and fumes with a distinct odor. For interior applications the building area must be vented with fresh air to dissipate the odor. The amount of air flow and time for venting will vary based on each situation. A closed attic area may require fans to force air into and out of the space. An open building that does not have the doors and windows installed may have sufficient air flow to vent the odor fairly quickly. Reentry time for closed-in areas being vented with fans is typically about 24 hours. Other workers should remain out of the immediate area during this venting time period.

The information on our data sheets is to assist customers in determining whether our products are suitable for their applications. The customers must satisfy themselves as to the suitability for specific cases. Profoam warrants only that the material shall meet its specifications. This warranty is in lieu of all other written or unwritten, expressed or implied warranties, and Profoam expressly disclaims any warranty of merchantability, fitness for a particular purpose, or freedom from patent infringement. Accordingly, buyer assumes all risks whatsoever as to the use of the material. Buyer's exclusive remedy as to any breach of warranty, negligence or other claim shall be limited to the purchase price of the material. Failure to adhere to any recommended procedures shall relieve Profoam of all liability with respect to the material or the use thereof.